





Amendments to the claims:

Please amend claim 1 and 18 as follows:

 Claim 1. (Previously Amended): A laminated extruded resin sheet comprising a methyl methacrylate resin produced by laminating resin layers (B) on both surfaces of a resin layer (A) by a multilayer-extrusion molding method, the resin layer (A) comprising a methyl methacrylate resin, and the resin layer (B) being made by dispersing uniformly 1 to 50 parts by weight of insoluble methyl methacrylate resin particles having a weight-average particle size of 1.0 to 33 μm based on 100 parts by weight of a base resin comprising a methyl methacrylate resin, said insoluble methyl methacrylate resin particles comprising 50% or more by weight of methyl methacrylate.

 Claim 18. (Previously Amended): A laminated extruded resin sheet comprising a methyl methacrylate resin produced by laminating resin layers (B) on both surfaces of a resin layer (A) by a multilayer-extrusion molding method, the resin layer (A) comprising a methyl methacrylate resin, and the resin layer (B) being made by dispersing uniformly 1 to 50 parts by weight insoluble methyl methacrylate resin particles having a weight-average particle size of 1.0 to 33 μm based on 100 parts by weight of a base resin comprising a methyl methacrylate resin, wherein a layer thickness ratio of resin layer (B)/resin layer (A)/resin layer (B) is from 1/200/1 to 1/1/1, and wherein the base resin comprises 100 parts by weight of a methyl methacrylate resin and 5 to 70 parts by weight of a rubber-containing polymer, said insoluble methyl methacrylate resin particles comprising 50% or more by weight of methyl methacrylate.

 Claim 24 (New): The laminated extruded resin sheet according to claim 1, wherein the resin layer (A) has no insoluble methyl methacrylate particles.

 Claim 25 (New): The laminated extruded resin sheet according to claim 18, wherein the resin layer (A) has no insoluble methyl methacrylate particles.